

Page 1/2

## **AQUASMART® -BITUMEN EMULSION**

## **Bitumen Emulsion Sealer and Damp-proofer**

#### DESCRIPTION

**AQUASMART®-BITUMEN EMULSION** is a thixotropic, premium, quick setting bitumen emulsion for damp-proofing below grade foundation and walls as well as wet rooms and under tile applications.

Apply with brush, roller or airless spraying in one or two coats with minimum total consumption of  $2-3~kg/m^2$  optionally reinforced with geotextile fabric available from Alchimica .

## **COMPLIANCE - CERTIFICATION**

The product is **CE** certified according to the European Standard **EN:1504-2:2004** 

## **LIMITATIONS**

Not recommended for:

· Unsound substrates,

## **FEATURES & BENEFITS**

- Easy to apply & repair.
- Thixotropic
- · Seamless.
- · Quick setting

## **APPLICATION PREREQUISITES**

#### Standard concrete substrate conditions

Hardness: R<sub>28</sub> = 15 Mpa.
Humidity: W < 10%.</li>
Temperature: 5-35 °C.
Relative humidity: < 85%.</li>

#### **APPLICATION PROCEDURE**

Clean the substrate using a high pressure washer, if possible. Remove oil, grease and wax contaminants. Cement laitance, loose particles, mould release agents, cured membranes must also be removed. Surface irregularities should also be filled. For optimum adhesion, surface should be damp but free of ponding water. The first coat is recommended to be thinned with 20% water to further aid adhesion.

#### **Application:**

Mix contents of the pail thoroughly before application. Apply the first coat diluted 20% with water. For optimum results embed a layer of polyester reinforcement and broom in immediately. Apply second coat as soon as base coat is dry to touch.

Do not apply under conditions of wet weather or expected wet weather.

## CONSUMPTION

Minimum total consumption: 1-4 kg/m<sup>2</sup> depending on application.

## CLEANING

Clean tools and equipment with water.

## SHELF LIFE

Can be kept for 6 months minimum in the original unopened pails in dry places and at temperatures of 5-25 °C. Do not allow content of pail to freeze.

#### **SAFETY INFORMATION**

The MSDS (Material Safety Data Sheet) is available on request.



Page 2/2

# **AQUASMART® -BITUMEN EMULSION**

TECHNICAL SPECIFICATIONS				
PROPERTY	UNITS	METHOD	SPECIFICATION	
Viscosity (Brookfield)	сР	ASTM D2196-86, @ 25 °C	15-20,000cps	
Specific weight	gr/cm³	ASTM D1475 / DIN 53217 / ISO 2811, @ 20 °C	1	
Required application temperature	°C	-	> 5	
Penetration on base asphalt	MIN	ASTM DS	80-100	
Dry time to touch	hrs	-	6	

CE				
21				
ALCHIMICA A.E.				
7 Lampsakou, Athens, Greece				
2085-CPR-082				
EN 1504-2:2004				
2085				
AQUASMART® BITUMEN EMULSION				
Concrete surface protection systems – Coating				
www.alchimica.com				

Essential characteristics	Performance	Harmonized technical specification	
CO₂ permeability, m	s <sub>D</sub> > 50		
Permeability to water vapor, m	s <sub>D</sub> < 5, class I		
Capillary absorption, kg/m²-h <sup>0.5</sup>	w< 0.1		
Bond strength by pull-off test, N/mm <sup>2</sup>	≥ 1.5	EN 1504-2:2004	
Impact resistance, N	≥ 4, class I		
Reaction to fire	Euroclass F		

NONE OF OUR PUBLISHED INSTRUCTIONS AND SPECIFICATIONS, IN WRITING OR OTHERWISE, ARE BINDING EITHER IN GENERAL OR WITH RESPECT TO ANY THIRD PARTY RIGHTS, OR DO THEY RELIEVE INTERESTED PARTIES OF THEIR DUTY TO SUBJECT THE PRODUCT TO AN ADEQUATE EXAMINATION OF ITS SUITABILITY. IN NO EVENT WILL ALCHIMICA S.A. BE RESPONSIBLE FOR DAMAGES OF ANY NATURE, WHATSOEVER, RESULTING FROM THE USE OF OR RELIANCE UPON INFORMATION OR THE PRODUCT TO WHICH INFORMATION REFERS. ALCHIMICA S.A. RESERVES THE RIGHT TO CHANGE AT ANY TIME THE PROPERTIES OF ITS PRODUCTS. PLEASE REFER TO THE CURRENT VERSION OF THE TECHNICAL DATA SHEET, AVAILABLE FROM OUR WEB SITE <a href="https://www.alchimica.com">www.alchimica.com</a>

