

Page 1/6

### **HYPERDESMO® AQUA**

 $C \in$ 

ETA-17/0922

# Very Fast Drying, Water based, One Component, Fully Aliphatic Polyurethane Coating for Waterproofing and Protection

#### **DESCRIPTION**

HYPERDESMO® AQUA based on ALCHIMICA's innovative water based polyurethane dispersion protects technology, structures environmental way, offering waterproofing in the most difficult conditions. HYPERDESMO® AQUA provides excellent resistance to ponding water with high resistance to difficult weather conditions and as it is aliphatic, it offers excellent resistance to UV radiation and improves the energy performance of a building by reducing surface temperatures. It is thixotropic, with excellent workability and quick drying which makes it easy to apply to a variety of substrates such as concrete or metal ceilings, polyurethane foam, etc. It is easily applied by brush, roller or spray in two or more coats on both vertical and horizontal substrates, forming an elastic and hydrophobic film.

The product can be used with a second component (booster) during cold weather for faster curing.

#### **COMPLIANCE - CERTIFICATION**

• **CE:** EN 1504-02:2004 No: 2928-CPR-55

• **CE**: ETA-17/0922

• **CE**: EN 14891:2012 (type DM 02P)

#### RECOMMENDED FOR

Waterproofing, Painting and Protection of:

- PU foam,
- · Roofs,
- · Light roofing made of metal or fibrous cement,
- Under tile applications such as wet rooms
- Protection of concrete/reinforced concrete from carbonization

#### LIMITATIONS

Not recommended for:

 Unsound substrates: (in some cases, application is possible with the use of geotextile reinforcement; please contact our technical department for consultations).

#### **FEATURES & BENEFITS**

- · Water based
- Very fast drying
- · Easy to apply & repair.
- Thixotropic
- · Seamless.
- Elastic.
- Highly resistant to stagnating water (ensure proper adhesion-see suitable primers list).
- Water vapor transmission: The film breathes so there is no accumulation of humidity under the coat.
- Excellent weather and UV resistance. The white color reflects much of the solar energy and so reduces the internal temperature of structures considerably.
- Easy coloring of product with almost any waterbased pigment paste available at hardware stores, subject to adequate tests.
- Compatible with all standard ALCHIMICA's Primers.

#### **APPLICATION PREREQUISITES**

#### Can be successfully applied on:

Concrete, fibrous cement, cement roof tiles, wood, galvanized steel, PU foam. For information about other substrates, please contact our tech department.



Page 2/6

### **HYPERDESMO® AQUA**



ETA-17/0922

#### Standard concrete substrate conditions:

Hardness: R28 = 15 Mpa.
Humidity: W < 10%.</li>
Temperature: 5-35 °C.
Relative humidity: < 85%.</li>

Suitable primers: AQUADUR, AQUASMART®-DUR, AQUASMART®-PU PRIMER-2K or MICROSEALER-50, depending on the substrate. Please contact our technical department for primer selection advice.

#### **APPLICATION PROCEDURE**

Clean the substrate using a high-pressure washer, if possible. Remove oil, grease and wax contaminants. Cement laitance, loose particles, mould release agents, cured membranes must also be removed. Surface irregularities should also be filled.

#### **Priming:**

Apply recommended primer according to Technical Data Sheet specifications.

For non- demanding applications (where standing water or negative water pressure is not an issue) prime with same material by diluting with 15% water. For more professional applications, apply primers as per above list or contact our technical department for further information.

#### Mixing:

Use a low speed (300 rpm) mixer.

#### Application:

Apply with roller, brush or airless spraying in two or more coats.

Do not apply under conditions of extreme wet weather or imminent rain or near freezing temperature.

#### **CONSUMPTION**

- Applied with roller or brush -First coat: 0.6-0.8 kg/m².
   Second coat: 0.6-0.9 kg/m².
- Applied by airless spraying: 0.5 kg/m² per coat. Minimum total consumption: >1.5 kg/m² for waterproofing, depending on project requirements. For use as a protective paint, recommended consumption is 0,5 Kg/m².

#### **CLEANING**

Clean tools and equipment immediately with water.

#### **PACKAGING**

Plastic pails of 5kg, 12 kg

#### SHELF LIFE

Can be kept for 12 months minimum in the original unopened pails in dry places and at temperatures of 5-25 °C. Once opened, use as soon as possible. Protect from freezing conditions.

#### **SAFETY INFORMATION**

The MSDS (Material Safety Data Sheet) is available on request.



Page 3/6

### **HYPERDESMO® AQUA**



ETA-17/0922

#### **TECHNICAL SPECIFICATIONS**

#### In liquid form (before application):

PROPERTY	UNITS	METHOD	SPECIFICATION
Viscosity (Brookfield)	сР	ASTM D2196-86, @ 25 ℃	20,000-40,000
Specific weight	gr/cm³	ASTM D1475 / DIN 53217 / ISO 2811, @ 20 °C	1.45-1.55
Required application temperature	۰C	-	> 5

#### In cured form (after application):

PROPERTY	UNITS	METHOD	SPECIFICATION
Service temperature	°C	-	-20 to 90
Hardness	Shore A	ASTM D2240 / DIN 53505 / ISO R868	70
Tensile strength at break @ 23 °C	Kg/cm <sup>2</sup> (N/mm <sup>2</sup> )	ASTM D412 / EN-ISO-527-3	50 (5.0)
Elongation @ 23 °C	%	ASTM D412 / EN-ISO-527-3	> 300
H <sub>2</sub> O absorption	%	-	< 5
QUV Accelerated Weathering Test (4hr UV, @ 60 °C (UVB- Lamps) & 4hr COND @ 50 °C)	-	ASTM G53	passed (2,000 hours)



Page 4/6

## HYPERDESMO® AQUA



ETA-17/0922

CLASSIFICATION ACCORDING TO EN 1504-02

CE		
22		
ALCHIMICA S.A.		
7 Lampsakou, Athens-GREECE		
2928-CPR-55		
EN 1504-2:2004		
2928		
HYPERDESMO® AQUA		
Product for protection and repair of concrete structures		
www.alchimica.com		

Essential characteristics	Performance	Harmonized technical specification
CO <sub>2</sub> permeability, m	S <sub>D</sub> >50	
Permeability to water vapor, m	S <sub>D</sub> <5 Class I	
Capillary absorption, kg/m <sup>2</sup> ·h <sup>0.5</sup>	w<0.1	
Adhesion strength by pull-off test, N/mm <sup>2</sup>	≥1.5	EN 1504-2:2004
Abrasion resistance, mg	<3000	
Impact resistance, N.m	≥4 Class I	
Reaction to fire	Euroclass F	



Page 5/6

### **HYPERDESMO® AQUA**



ETA-17/0922

CLASSIFICATION ACCORDING TO EOTA (EUROPEAN ORGANISATION OF TECHNICAL APPROVAL

CE
24
ALCHIMICA S.A.
7 Lampsakou, Athens-GREECE
17/0922
EAD 030350-00-0402
1219
HYPERDESMO® AQUA
Liquid Applied Roof Waterproofing Kit based on Polyurethane.
www.alchimica.com

Essential characteristics	Performance	Harmonized technical	
		specification	
Minimum thickness	1.6mm	EAD 030350-00-0402	
Water vapour diffusion resistance		EAD 030350-00-0402	
factor (µ)	~890		
Resistance to wind loads	>50KPa	EAD 030350-00-0402	
Statement on dangerous		EAD 030350-00-0402	
substances	Does not contain any		
External fire performance	NPD	EAD 030350-00-0402	
Expected working life	W2 (10 Years)	EAD 030350-00-0402	
Climatic zone of use	S (Severe)	EAD 030350-00-0402	
User loads	P1 to P3 (P3 REINFORCED)	EAD 030350-00-0402	
Roof slopes	S1 to S4	EAD 030350-00-0402	
Minimum surface temperatures	TL3 (-20°C)	EAD 030350-00-0402	
Maximum surface temperatures	TH4 (90°C)	EAD 030350-00-0402	



Page 6/6

### HYPERDESMO® AQUA



ETA-17/0922

#### **CLASSIFICATION ACCORDING TO EN 14891**



24

#### **ALCHIMICA S.A.**

7 Lampsakou, Athens-GREECE 1020-CPR-020050844

EN 14891:2012

1020

#### HYPERDESMO® AQUA

Dispersion liquid-applied water impermeable product for use beneath ceramic tiling bonded with adhesives.

www.alchimica.com

Essential characteristics	Performance	Requirement	Harmonized technical specification
Water tightness	No penetration	No penetration	
Crack bridging ability under standard conditions (23°C)	2.29 mm	≥0.75 mm	
Crack bridging ability at low temperatures (-5°C)	1.55 mm	≥0.75 mm	
Crack bridging ability at low temperatures (-20°C)	1.36 mm	≥0.75 mm	EN 14891:2012
Initial bond strength	0.88 N/mm <sup>2</sup>	≥0.5 N/mm <sup>2</sup>	
Bond strength after water immersion	1.04 N/mm²	≥0.5 N/mm²	
Bond strength after heat ageing	1.01 N/mm <sup>2</sup>	≥0.5 N/mm <sup>2</sup>	
Bond strength after freeze-thaw cycles	1.22 N/mm <sup>2</sup>	≥0.5 N/mm²	
Bond strength after contact with lime water	0.52 N/mm <sup>2</sup>	≥0.5 N/mm²	
Bond strength after contact with chlorinated water	0.98 N/mm <sup>2</sup>	≥0.5 N/mm²	

NONE OF OUR PUBLISHED INSTRUCTIONS AND SPECIFICATIONS, IN WRITING OR OTHERWISE, ARE BINDING EITHER IN GENERAL OR WITH RESPECT TO ANY THIRD PARTY RIGHTS, OR DO THEY RELIEVE INTERESTED PARTIES OF THEIR DUTY TO SUBJECT THE PRODUCT TO AN ADEQUATE EXAMINATION OF ITS SUITABILITY. IN NO EVENT WILL ALCHIMICA S.A. BE RESPONSIBLE FOR DAMAGES OF ANY NATURE, WHATSOEVER, RESULTING FROM THE USE OF OR RELIANCE UPON INFORMATION OR THE PRODUCT TO WHICH INFORMATION REFERS. ALCHIMICA S.A. RESERVES THE RIGHT TO CHANGE AT ANY TIME THE PROPERTIES OF ITS PRODUCTS. PLEASE REFER TO THE CURRENT VERSION OF THE TECHNICAL DATA SHEET, AVAILABLE FROM OUR WEB SITE <a href="https://www.alchimica.com">www.alchimica.com</a>

