

## PRIMER-T

### Single Component, Non Staining Primer for Non Porous Substrates

#### DESCRIPTION

**PRIMER-T** is one component, colorless, non-staining primer especially designed to secure the adhesion of **HYPERDESMO®-T** on non-porous substrates. Although designed for **HYPERDESMO®-T**, it is fully suited for all products in the **HYPERDESMO®** product range. Chemically, **PRIMER-T** is composed of a moisture reacting organosilane in a mixture of solvents and additives to ensure overall wetting of the substrate.

**PRIMER-T** is easily applied by wetting a clean cloth and essentially cleaning the surface to be protected with **HYPERDESMO®-T**.

**PRIMER-T** dries quickly; within 10-15 min max, the surface is ready for application.

#### RECOMMENDED FOR

Priming of non-porous substrates.

- Glazy tiles
- Glass

#### LIMITATIONS

- Apply minimal amount of primer by cloth
- Avoid pools, runs, and drips.



#### FEATURES & BENEFITS

- Quick drying.
- No thinning is required
- Non-Staining.
- Easy application

#### SURFACE PREPARATION

Clean the surface, using jet water if possible. Remove oil, grease and wax contaminants. Cement laitance, loose particles, mold release agents, curing membranes must be removed.

Apply the material with cloth as cleaning the surface. Allow 10-15 min for drying and subsequently apply **HYPERDESMO®-T**.

#### PRECAUTIONS

**PRIMER-T** contains volatile flammable solvents. Apply in well-ventilated areas. Do not smoke. Apply far away from naked flames. In closed areas use force ventilation and carbon active masks. Keep in mind that solvents are heavier than air so they creep on the floor.

Ask for MSDS (Material Safety Data Sheet)

#### CONSUMPTION

**Maximum total consumption: 50-60 ml/m<sup>2</sup> .**

#### PACKAGING

1lt, 5 lt, 20 lt

#### SHELF LIFE

**PRIMER-T** can be kept for minimum 12 months in the original unopened pails at a temperature of 5 °C - 25 °C in dry places.

## PRIMER-T

### TECHNICAL SPECIFICATIONS OF PRIMER-T

#### **The Liquid product:**

PROPERTY	UNITS	METHOD	SPECIFICATION
-Viscosity (BROOKFIELD)	cP	ASTM D2196-86, at 25°C	30-50
-Specific weight	gr/cm <sup>3</sup>	ASTM D1475 / DIN 53217 / ISO 2811, at 20°C	0.80-0.90
-Flash point	°C	ASTM D93, Closed cup	42
-Dry time at 77deg F (25°C) & 55% RH	min	-	10-15

NONE OF OUR PUBLISHED INSTRUCTIONS AND SPECIFICATIONS, IN WRITING OR OTHERWISE, ARE BINDING EITHER IN GENERAL OR WITH RESPECT TO ANY THIRD PARTY RIGHTS, OR DO THEY RELIEVE INTERESTED PARTIES OF THEIR DUTY TO SUBJECT THE PRODUCT TO AN ADEQUATE EXAMINATION OF ITS SUITABILITY. IN NO EVENT WILL ALCHIMICA™ S.A. BE RESPONSIBLE FOR DAMAGES OF ANY NATURE, WHATSOEVER, RESULTING FROM THE USE OF OR RELIANCE UPON INFORMATION OR THE PRODUCT TO WHICH INFORMATION REFERS.

